



Parameter	Unit	Test Method	Typical Values
Colour ASTM		ISO 2049	1.0 - 2.0
Density 15°C	kg/m <sup>3</sup>	EN ISO 12185	860 - 870
Viscosity 40°C	mm <sup>2</sup> /s	EN ISO 3104	40 - 46
Viscosity 100°C	mm <sup>2</sup> /s	EN ISO 3104	6.4 - 7.1
Viscosity Index		ISO 2909	110 - 115
Neutralization Number	mg KOH/g	DIN 51 558-1	≤ 0.03
Flashpoint COC	°C	ISO 2592	> 230
Pour Point	°C	ISO 3016	≤ -9
Noack Evaporation Loss	wt. %	DIN 51 581	5 - 9
Sulfur	wt. %	EN ISO 14596	≤ 0.25
Copper Corrosion	3h/100°C	EN ISO 2160	1
C <sub>A</sub>	%	DIN 51 378-K	2

This data sheet and the information it contains is believed to be accurate as of the date of printing. However, no warranty or representation, express or implied, is made as to its accuracy or completeness. Data provided is based on standard tests under laboratory conditions and is given as a guide only. Users are advised to ensure that they refer to the latest version of this data sheet. It is the responsibility of the user to evaluate and use products safely, to assess suitability for the intended application and to comply with all applicable laws and regulations. Material Safety Data Sheets are available for all our products and should be consulted for appropriate information regarding storage, safe handling, and disposal of the product. No responsibility is taken by either AVISTA OIL Group or its subsidiaries for any damage or injury resulting from abnormal use of the material, from any failure to adhere to recommendations, or from hazards inherent in the nature of the material. All products, services and information supplied are provided under our standard conditions of sale.

**Contact:****AVISTA OIL Refining & Trading Deutschland GmbH**

Bahnhofstraße 82, 31311 Uetze, Germany

Tel. +49 5177 85-119

Fax +49 5177 85-230